

Progress on LHE Zinc-Nickel and Other Cadmium Alternatives

Steve Gaydos – Boeing – St. Louis, MO

Craig Pessetto – ES3 – Clearfield, UT

Jay Randolph – ES3 – Warner Robins, GA

ASETSDefense 2009

Sustainable Surface Engineering for Aerospace and Defense

September 3, 2009

Westminster, CO

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 03 SEP 2009		2. REPORT TYPE		3. DATES COVERED 00-00-2009 to 00-00-2009	
4. TITLE AND SUBTITLE Progress on LHE Zinc-Nickel and Other Cadmium Alternatives				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Boeing,P. O. Box 516,St. Louis,MO,63166				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES ASETSDefense 2009: Sustainable Surface Engineering for Aerospace and Defense Workshop, August 31 - September 3, 2009, Westminster, CO. Sponsored by SERDP/ESTCP.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 35	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

Cadmium Alternatives

- Zinc-Nickel (ES3 and Boeing)
 - Dipsol IZ-C17+ Alkaline Zinc-Nickel Plating
 - Tank Install at Hill AFB
 - Evaluation of Zn-Ni on Fasteners
- Aluminum (Boeing)
 - Sputter Aluminum
 - Cold Spray Aluminum
 - Aluminum Plating with Ionic Liquids

Dipsol Zinc-Nickel History

- 1996 – 2000 (WPAFB – ASC/ENVV)
 - Evaluated IZ-260 (In Use at DoD Plating Facilities)
 - Required Nickel Strike to be Non-Embrittling for HSS
- 2003 – 2005 (C-17 Pollution Prevention)
 - Developed IZ-C17 Alkaline Zn-Ni for HSS
 - No Ni Strike and Non-Embrittling to High Strength Steels (HSS)
- 2006 – 2007 (C-17 Pollution Prevention)
 - Conducted Qualification Tests for IZ-C17 Zn-Ni
- 2008 (ES3 – SBIR – Phase I)
 - Evaluated **IZ-C17+** Zn-Ni (Better Tank Life Than IZ-C17)
 - Also Compared TriCr CC with Hex Cr CC
- **2009 (ES3 – SBIR – Phase II)**
 - **Installed Plating Tank with IZ-C17+ Zinc-Nickel at Hill AFB**
 - **Also Installed IZ-264 Tri-Cr CC**
- **2009 (ES3 – SBIR – Phase I)**
 - **IZ-C17+ Zn-Ni Fasteners Feasibility Study**

Dipsol IZ-C17+ Zn-Ni Tank Installation at Hill AFB

April 27-28, 2009

Plating Line @ Hill AFB



Alkaline Zn-Ni Plating Tank Installation



Trivalent Cr Conversion Coating Tank Installation



Dipsol IZ-C17+ Zn-Ni Chemicals & Rectifier



IZ-C17+ Zi-Ni Tank @ Hill AFB





IZ-264 TriCr Conversion Coat Tank @ Hill AFB



IZ-C17+ Tank Certification Tests


- Hydrogen Embrittlement
 - Pass
 - ASTM F 519 Type 1a.1
- Thickness and Adhesion
 - Pass
 - 0.3 to 0.6 mil
 - Bend-to-Break Adhesion
- Corrosion Resistance - Pass
 - 1000 hour ASTM B 117



Current Testing at Hill AFB

- ASTM B 117 Corrosion Tests
- ASTM G 85 (SO₂) Corrosion Tests
- Fatigue and Hydrogen Embrittlement Testing at Different Zn and Ni Concentrations
- Develop Rapid HE Test Methods
 - Following ASTM F 1624 Guidelines
- Conduct Full Scale Plating Tests
 - Large Landing Gear Parts

ASTM B 117 Corrosion




IZ-C17+ Zn-Ni – 3000 Hrs in ASTM B 117




LHE Cadmium – 500 Hrs in ASTM B 117

ASTM G 85 Corrosion




IZ-C17+ Zn-Ni – 336 Hrs in ASTM G 85 – SO₂ Salt Spray




LHE Cadmium – 336 Hrs in ASTM G 85 – SO₂ Salt Spray

ASTM G 85 Corrosion



Painted - IZ-C17+ Zn-Ni – 1000 Hrs in ASTM G 85 – SO₂ Salt Spray



Painted - LHE Cadmium – 1000 Hrs in ASTM G 85 – SO₂ Salt Spray

Development of Cad Plating Replacement with Alkaline Zn-Ni Electroplating for Threaded Fasteners / Components

Jay Randolph
ES3

(478) 922-1460

jay.randolph@es3inc.com

Fred Laguines
ES3

(478) 922-1460

fred.laguines@es3inc.com

Don Crawford
ES3

(478) 922-1460

don.crawford@es3inc.com

Steve Gaydos
Boeing - St. Louis
(314) 233-3451

stephen.gaydos@boeing.com

Development of Cad Plating Replacement with Alkaline Zn-Ni Electroplating for Threaded Fasteners / Components


Acknowledgement of Support and Disclaimer

ES3 would like to acknowledge the US government's support in the publication of the SBIR related material developed under this contract. All SBIR related material is based upon work supported by the United States Air Force under Contract No. FA8501-08-M-0108. Any opinions, findings and conclusions or recommendations expressed in this material are those of the authors and do not necessarily reflect the views of the United States Air Force.

Project Summary

- Feasibility Study was completed by ES3 in April 2009.
 - Used Barrel Plating Technique on threaded steel fasteners.
 - Used Dipsol IZ-C17+ Zn-Ni
 - Excellent coverage and uniformity.
 - ASTM B 117 Corrosion Test on Fasteners
 - IZ-C17+ Zn-Ni equal to or better than Cd plated fastener baseline
 - Lubricity Tests: Run-On-Break-Away Test & Torque Tension
 - Baseline was Cd plate
 - 13 Lubricants tested
 - Zn-Ni performed as well or better than Cd plating in testing
- Phase II Test program scheduled to start in 1st Qtr FY10.
 - Qualify low alloy steel fasteners with Alkaline Zn-Ni Plating
 - Options, when funding is available, to conduct HSS 300M Steel threaded component testing with rack plating technique & qualify HSS low alloy steel fasteners.
- ES3 is working with Boeing St. Louis on this effort.
- SBIR #AF081-101 is sponsored by Robins AFB.

Dipsol IZ-C17+ Zn-Ni Barrel Plating of Fasteners







Zn-Ni and Cd Plated Fasteners

- View of:
 - Zn-Ni Plated Fasteners with Tri-Chrome Conversion Coating (top)
 - Cadmium Plated Fasteners with Hex-Chrome Conversion Coating (bottom)



Zn-Ni and Cd Plated Fasteners - Corrosion Testing




- Corrosion Photos after 1000 Hours in ASTM B 117 Salt Spray Cabinet
 - Left is Fully Painted Aluminum Test Panel with Nut
 - Right is Partially Painted Aluminum Test Panel with Bolt


Zn-Ni and Cd Plated Fasteners – Lubricity Testing

- Typical Chart for Run On - Break Away Test Showing Cad vs Alkaline Zn-Ni with and without MIL-PRF-83483 Anti-Seize Grease Lubricant


Typical Run-On & Breakaway Torque - Cad Bare




Typical Run-On & Breakaway Torque - Zn-Ni Bare



Typical Run-On & Breakaway Torque - w/ Cad Anti-Seize Grease




Typical Run-On & Breakaway Torque - Zn-Ni w/ Anti-Seize Grease




Zn-Ni and Cd Plated Fasteners – Lubricity Testing

- Typical Chart for Torque Tension Test Showing Cad vs Alkaline Zn-Ni with and without MIL-PRF-83483 Anti-Seize Grease Lubricant


Typical Torque Tension - Cad Bare




Typical Torque Tension - Zn-Ni Bare



Typical Torque Tension - Cad w/ Anti-Seize Grease




Typical Torque Tension - Zn-Ni w/ Anti-Seize Grease




Zn-Ni and Cd Plated Fasteners – Metallography


- Typical Cross Section of Zn-Ni and Cadmium Plated NAS 6606-10 Bolt.



Zn-Ni Flat Surface Cd



Zn-Ni Thread Crest Cd



Zn-Ni Thread Root Cd


Cross-Sections of Long Bolt

Aluminum Coatings

Sputter Aluminum

- Plug & Coat Sputter Probes (ID Coating)
 - Developed by Marshall Laboratories (Boulder, CO)
 - Installed in IVD Coater at Hill AFB
 - Process Certified by Boeing (DPS 9.22-1)
 - ES3 Currently Investigating New Sputter Probe Application at Hill AFB
- S-PAC (Small Parts Aluminum Coater)
 - Equipment Currently Being Built to Apply Sputter Aluminum Coating to OD of Parts
 - Update of IVD Process

Plug & Coat Sputter Probe Operation



Cold Spray Aluminum

- Centerline SST Cold Spray Equipment
 - Installed at Boeing – July 2008
 - Procedures Developed to Apply Cold Spray Aluminum Coating (1 - 2 mils)
 - Repair Damaged MIL-DTL-83488 Aluminum Coatings (IVD, Sputter, CVD, Alumiplate, etc.)
 - Demonstration of Cold Spray Technology Held at Boeing on August 13, 2009

Centerline SST Portable Cold Spray Equipment



Centerline Ultra-Portable Cold Spray Equipment



Trained Cold Spray Operators



Best Dressed Cold Spray Operator



Oldest Cold Spray Operator


IVD AI Repaired with Cold Spray AI



Damaged IVD AI



Damaged Area Prepared



Cold Spray AI Repaired IVD AI


Cold Spray Aluminum – Corrosion Resistance



1000 Hours in ASTM B 117 (Scribed Corrosion Test) –
Cold Spray Al on Steel (Left) and Cold Spray Al on Damaged IVD Al (Right)

Aluminum Plating in Ionic Liquids

- Boeing Research & Technology – Europe
Evaluating Ionic Liquids for Aluminum Plating



Questions?